

郑州市海旭磨料有限公司
河南省荥阳市高村乡工业园区
<http://www.sichx.com>

TECHNICAL DATA SHEET

品名: 黑碳化硅/黑色金刚砂 **粒度:**F12-F220
碳化硅，化学式为 SiC，是用石英砂、石油焦（或煤焦）、木屑（生产绿色碳化硅时需要加食盐）等原料通过电阻炉高温冶炼而成。具有高强度，高硬度，耐磨，耐腐蚀，抗氧化，高热导率，良好的高温稳定性，耐腐蚀性等

<u>化学成分(典型值)</u>				<u>物理特性(典型值)</u>			
SiC		≥98. 6%		密度	≥3. 12g/cm ³		
F. C		≤0. 20%		莫氏硬度	9. 15		
Fe ₂ O ₃		≤0. 40%		熔点	2250°C		
SiO ₂		≤0. 05%		磁性物含量	≤0. 025%		

粒度分布行业标准

12 目/F12	+2800μm	0	+2000μm	≤20%	+1700μm	≥45%	+1700+1400μm	≥70%	-1180μm	≤3%
14 目/F14	+2360μm	0	+1700μm	≤20%	+1400μm	≥45%	+1400+1180μm	≥70%	-1000μm	≤3%
16 目/F16	+2000μm	0	+1400μm	≤20%	+1180μm	≥45%	+1180+1000μm	≥70%	-850μm	≤3%
20 目/F20	+1700μm	0	+1180μm	≤20%	+1000μm	≥45%	+1000+850μm	≥70%	-710μm	≤3%
F22	+1400μm	0	+1000μm	≤20%	+850μm	≥45%	+850+710μm	≥70%	-600μm	≤3%
24 目/F24	+1180μm	0	+850μm	≤25%	+710μm	≥45%	+710+600μm	≥65%	-500μm	≤3%
30 目/F30	+1000μm	0	+710μm	≤25%	+600μm	≥45%	+600+500μm	≥65%	-425μm	≤3%
36 目/F36	+850μm	0	+600μm	≤25%	+500μm	≥45%	+500+425μm	≥65%	-355μm	≤3%
46 目/F46	+600μm	0	+425μm	≤30%	+355μm	≥40%	355+300μm	≥65%	-250μm	≤3%
54 目/F54	+500μm	0	+355μm	≤30%	+300μm	≥40%	+300+250μm	≥65%	-212μm	≤3%
60 目/F60	+425μm	0	+300μm	≤30%	+250μm	≥40%	250+212μm	≥65%	-180μm	≤3%
70 目/F70	+355μm	0	+250μm	≤25%	+212μm	≥40%	+212+180μm	≥65%	-150μm	≤3%
80 目/F80	+300μm	0	+212μm	≤25%	+180μm	≥40%	+180+150μm	≥65%	-125μm	≤3%
90 目/F90	+250μm	0	+180μm	≤20%	+150μm	≥40%	+150+125μm	≥65%	-106μm	≤3%
100 目/F100	+212μm	0	+150μm	≤20%	+125μm	≥40%	+125+106μm	≥65%	-75μm	≤3%
120 目/F120	+180μm	0	+125μm	≤20%	≥40%	≥40%	+106+90μm	≥65%	-63μm	≤3%
150 目/F150	+150μm	0	+106μm	≤15%	+75μm	≥40%	+75+63μm	≥65%	-45μm	≤3%
180 目/F180	+125μm	0	+90μm	≤15%	+75μm+63μm	≥40%	+75μm+63μm+53μm	≥65%		
220 目/F220	+106μm	0	+75μm	≤15%	+63μm+53μm	≥40%	+63μm+53μm+45μm	≥60%		

包装: 25 千克小袋+吨包/托盘缠膜

联系人: 马九玲

手机/微信: 15838373120

Email:sales@zzhai xu. cn